All values listed are target values

2" core



IJM119 Premium Paper - FSC® 100 g/m²



Product Description

IJM119 is a high-quality matt coated paper recommended for presentation quality CAD and GIS drawings with solid colour fills.

Physical Properties

Thickness	120 μm	ISO 534
Weight	100 g/m ²	ISO 536
Smoothness (Bekk)	100 s	ISO 5627
Opacity	>88%	ISO 2471

Brightness (R457+)	>95 %	ISO 2470-2
Tensile strength MD/CD	>4.0/1.5 kN/m	ISO 1924-1
Tearing strength MD/CD	>600/600 mN	ISO 1974

Applications/ features

Colour and monochrome CAD and GIS High-quality standard and presentation drawings Presentation quality Excellent dot gain Superior line sharpness Good contrast Good smear resistance FSC certified

Avai	lab	е
Widths ((mn	1)

Refer for our current offering to www.canon-europe.com/mediaquide

841

610

Storage Conditions

Temperature 10-30°C, Relative Humidity 20-80%

594

Repack opened rolls when not in use.

Print Conditions

Best results are obtained between 15-25°C and 30-70% RH. Correct maintenance of cartridges or print heads will result in optimal print quality. Please check your printer documentation for recommended maintenance.

914

1067

Environment, Health & Safety

No Material Safety Data Sheet required. Waste can be handled as paper waste.

Lamination Compatibility

Cold	Warm	Hot
yes	yes	no

Cold: pressure sensitive Warm: heat activated: 85°C - 95°C Hot: heat activated: 105°C -130°C

Outdoor Use

This coated paper is not suitable for outdoor use.

Colour Profiles

Canon develops high-quality colour profiles for media / ink / printer / RIP combinations. Check availability of profiles for your printer on www.canon-europe.com/mediaquide

Environmental Certification





Processing Guidelines

Printing guidelines

Allow material to adapt to room conditions for 24 hours before printing. Side to be printed is the outer side of the roll.

Make sure that the media comes not into contact with grease, oil, silicon, and dirt to avoid printing defects. It is recommended to handle the media with cotton gloves.

Insert the paper with care in the printer. Incorrect loading can cause skewing or creasing. It is recommended to calibrate the printer before printing and to make a test print.

Print results will vary for different printer ink combinations. Ink restrictions and printer settings should be set for specific printer-ink combinations to obtain the best results. Canon media profiles include optimal ink and printer settings for Canon supported printers. Depending on fluctuations in environment, printer, ink, media and applications, printer parameters may have to be adjusted slightly, to obtain the best results.

Too much ink will cause paper cockle and possible head strikes. The use of dye inks can lead to premature fading of colors.

Application guidelines

The use of cold or warm laminates are recommended for the best results.

Allow the print to dry properly before to lamination. That is at least 24 hours. Too much ink can cause cockling which can cause problems with laminating. For mounting on a board, an encapsulating edge of 5-6mm around the image is recommended. This prevents against moisture and paper splitting because of the tension of the laminate. One sided lamination may cause curling. Use laminates of equal gauge when encapsulating to prevent image curl. Generally, lamination will only slightly improve UV resistance (pigmented inks should be used when UV resistance is required).

Standard disclaimer: All specifications subject to change without notice. All company and/or product names are trademarks and/or registered trademarks of their respective manufacturers in their markets and/or countries.

canon.com
Canon Europe
canon-europe.com
English edition 0615
© Canon Europa N.V., 2018

Canon Inc.

